

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.


Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**





**CERTIFICATE OF MAILING**

I hereby certify that this correspondence is being deposited with the United States Postal Service as First Class Mail in an envelope addressed to:

"Assistant Commissioner for Patents  
Washington, D.C. 20231"

on January 7, 2004

*Milton L. Honig*

MILTON L. HONIG

Reg. No. 28,617

Attorney for Applicant(s)

01/07/04

Date of

Signature

**PATENT**

#03-0101-UNI

Case #J7158(V)

**IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

Applicant: Davies et al.  
Serial No.: 10/665,230  
Filed: September 17, 2003  
For: BRUSH DEVICE

Edgewater, New Jersey 07020  
January 7, 2004

**SUBMISSION OF PRIORITY DOCUMENT**

Assistant Commissioner for Patents  
Washington, D.C. 20231

Sir:

Pursuant to rule 55(b) of the Rules of Practice in Patent Cases, Applicant(s) is/are submitting herewith a certified copy of the European Application No. 02079168.7 filed September 20, 2002, upon which the claim for priority under 35 U.S.C. § 119 was made in the United States.

It is respectfully requested that the priority document be made part of the file history.

Respectfully submitted,

*Milton L. Honig*

Milton L. Honig

Reg. No. 28,617

Attorney for Applicant(s)

MLH/mt  
(201) 840-2403





**Eur päisches  
Patentamt**

**European  
Patent Office**

**Office européen  
des brevets**

**Bescheinigung**

**Certificate**

**Attestation**

Die angehefteten Unterlagen stimmen mit der ursprünglich eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.

The attached documents are exact copies of the European patent application described on the following page, as originally filed.

Les documents fixés à cette attestation sont conformes à la version initialement déposée de la demande de brevet européen spécifiée à la page suivante.

**Patentanmeldung Nr.    Patent application No.    Demande de brevet n°**

**02079168.7**

Der Präsident des Europäischen Patentamts;  
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets  
p.o.

**R C van Dijk**





Eur päisch s  
Pat ntamt

Eur p an  
Pat nt Offic

Offic uropé n  
d br v ts

Anmeldung Nr:  
Application no.: 02079168.7  
Demande no:

Anmeldetag:  
Date of filing: 20.09.02  
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

UNILEVER N.V.  
Weena 455  
3013 AL Rotterdam  
PAYS-BAS

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:  
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.  
If no title is shown please refer to the description.  
Si aucun titre n'est indiqué se referer à la description.)

Brush device

In Anspruch genommene Priorität(en) / Priority(ies) claimed /Priorité(s)  
revendiquée(s)  
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/  
Classification internationale des brevets:

A46B9/04

Am Anmeldetag benannte Vertragstaaten/Contracting states designated at date of  
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR IE IT LI LU MC NL PT SE SK TR





J7158 (V) FF

- 1 -

Brush Device.

The invention provides a toothbrush comprising a resilient element into which is incorporated an abrasive.

5

WO 01/21036 (Unilever PLC) discloses a toothbrush with a wall-like element optionally with an abrasive.

WO 98/22000 (Asher) discloses a plaque removing member with an abrasive. This device aids in the removal of plaque during the brushing process.

US 5249961 (Hoagland) discloses a portable pet teeth cleaning instrument with an abrasive pad or sponge with an abrasive composition embedded in a phenolic resin and/or embedded in or adhered to nylon fibrous strands.

WO 99/60886 (Durana) discloses a toothbrush with a polishing block made from an elastic material and which can contain an abrasive material.

US 5273559 (Hammar) discloses the use of polyurea or polyurethane urea or a natural or synthetic rubber matrix with bonded abrasive particles. These articles are used in prophylactic cleaning cups for the use by high skilled dental practitioners.

US 2001/007161 (Gillette) and US 6199242 (Gillette) disclose a toothbrush with bristles containing a polishing agent to improve the cleaning of the teeth.

J7158 (V) FF

- 2 -

US 3618154 (Muhler) discloses a brush with bristles moulded integrally with the brush. This brush also has abrasive incorporated into the plastic material of the brush. A disadvantage of this is that the bristles when formed in  
5 this way are difficult to mould. This is because it is hard to structure a mould that results in narrow but structurally sound bristles.

US 4373541 (Nishioka) discloses the use of flexible bristles  
10 with abrasive elements such as scales, serrations, and the like formed from the bristle material in addition to abrasive particles on the side of the bristle itself.

US 6296934 B1 (Needham) discloses the use of glitter  
15 containing filaments for a brush.

None of this prior art discloses perlite as an abrasive.

US 6357075 (Kaizuka) discloses a hairbrush with bristles  
20 that contain an infrared material in combination with minerals, such as perlite, which radiate electromagnetic waves promoting hair growth, providing scalp care and creating shiny hair.

25 Hairbrush bristles have different physical properties when compared with toothbrush bristles and this represents their different function in parting hair along the bristles length during brushing. Hairbrush bristles are therefore wide enough to encompass abrasive particles such as perlite  
30 whereas toothbrush bristles, the ends of which are pointed for cleaning interstitial spaces between teeth, are very

J7158 (V) FF

- 3 -

different. A disadvantage of having toothbrush bristles with abrasive particles is that as the bristles are so thin that incorporated particles weaken the structure of the bristle filament. If the bristles of a toothbrush were made  
5 thicker to accommodate an abrasive they would lose the characteristics that make them useful as toothbrushes. Hence thicker bristles in a toothbrush are disadvantageously stiff due to their extra width and they would not be able to penetrate between the teeth. Therefore, simply making a  
10 toothbrush bristle thicker to accommodate the abrasive will not aid in the process cleaning teeth.

Despite the presence in the prior art of such brushes as outlined above, there is still a need for a toothbrush which  
15 is capable of providing improved whitening or stain removal benefit while retaining the cleaning and polishing capacity of the cleaning instrument.

According to the present invention there is provided a  
20 toothbrush comprising a resilient element, said resilient element comprising an elastomer into which is incorporated an abrasive, characterized in that the abrasive is perlite.

It has been found that the addition of perlite to an  
25 elastomer aids in the removal of stains from teeth. This improves the cleaning potential of toothbrushes, which encompass this element. This improves the toothbrush's ability to remove adherent soiling matter, to free accessible plaque, to dislodge accessible debris and to  
30 remove superficial stain from the teeth which in turn leads to improved mouthfeel and teeth whitening benefits.

J7158 (V) FF

- 4 -

Perlite comprises flat particles which, when they are incorporated into the molten elastomer, align with the surface of the elastomer when it cools. When the resilient element is pressed against the surface of the teeth for cleaning and it elastically deforms, the perlite is maintained in a substantially parallel alignment with the surface of the elastomer. This provides the surface of the elastomer with extra rigidity hence enhancing its cleaning efficacy.

10

The shape and alignment of the perlite particles on the surface of the elastomer means that they do not have jagged edges that protrude from the elastomer. Therefore the perlite particles in the elastomer do not damage surfaces such as teeth and soft tissue that they contact in the oral cavity. Perlite particles in the elastomer significantly enhance the cleaning potential of the resilient element so that in combination they provide for improved whitening effect without causing damage due to excessive abrasion.

20

The toothbrush according to the invention is for use in the oral cavity for cleaning teeth. The toothbrush according to the invention may be made from any materials commonly used in the art. Accordingly, the handle and head of the brush can be moulded from polyolefins such as polypropylenes and polyethylenes, polyamides such as nylons, and polyesters such as polyethylene terephthalate. Other suitable materials include polymethylmethacrylate, styrene acrylonitrile and cellulose esters, for example cellulose propionate.

30

J7158 (V) FF

- 5 -

The bristles of the brush may be made from a flexible material suitable for use in dental hygiene. Generally, materials suitable for the bristles are polyamides such as nylon or polyesters such as polybutylene terephthalate.

5

The brush according to the invention may be a manual toothbrush or an electrically driven toothbrush.

10 The resilient element may take the form of a pick, a finger, a prong, or a fork structure. According to a preferred embodiment the resilient element is wall-like. A wall-like structure allows for whitening or polishing benefit, as the wall-like structure can be elastically deformed thereby exerting pressure on the teeth for cleaning benefit while  
15 not exerting such a force as to damage the teeth. Similarly it can not just be moved to one side, as may be the case with a pick. In addition to this the wall-like structure may be designed to be of such a width that it effectively comprises perlite without compromising the stability and  
20 structure of the elastomer which makes up the wall-like element.

It is envisaged that the resilient element can be made by any conventional method, i.e. die-cut or moulded. However, a  
25 preferred method of making such a structure would be by injection moulding. The material of the resilient element may be linked to the head of the toothbrush in any way whether it is by chemical means, mechanical means or both.

30 Preferably the resilient element material is chemically compatible with the material of the head and they may be

J7158 (V) FF

- 6 -

joined by application of heat, e.g. during injection moulding of one or the other.

- Alternatively the materials may be chemically incompatible, e.g. the resilient element comprising a thermoplastic elastomer and the brush head comprising polypropylene. It may, therefore, be more suitable to use an adhesive or to mechanically attach the two parts to one another. An alternative method of attaching the resilient element comprising a thermoplastic elastomer to a head comprising polypropylene would be to increase the surface area of the area of attachment, e.g. by corrugating one or both, and then fixing the two together by welding or otherwise.
- 15 It may also be that the resilient element is contiguous with another portion of the brush comprising the same material and that both are filled through one or more injection points. For example, the resilient element and a grip region on the handle are contiguous through a channel running along the head to the handle.

- It may also be that the resilient element and the grip region on the handle have separate injection points so that the resilient element encompassing the perlite can be injected into the head region of the toothbrush while the grip region of the handle may not contain any perlite.

- The resilient element may be flanked by bristles. Such flanking may be a mere scattering of bristles but it is preferred that the bristles are located outermost on the brush head and the resilient element is located more

J7158 (V) FF.

- 7 -

centrally. This is a particularly beneficial design as it allows the teeth to be cleaned while also allowing the teeth to be polished. The bristles are flexed outwardly to allow the resilient element to contact the teeth and this further improves the cleaning efficacy of the brush. Should the resilient element be located at the outer edges of the brush head the flexing of the bristles would compromise the polishing and whitening capability of the brush.

10 To further enhance the benefit described above it is preferred that the bristles are longer than the resilient element. This ensures that the bristles extend further from the head than does the resilient element. This creates a recess in the center of the brush head which further allows the flexing of the bristles to effect good cleaning while allowing the resilient element to whiten the teeth.

The perlite in the resilient element according to the invention may be any perlite or mixtures of perlite commonly known in the art. It can be crude or non-expanded perlite. Preferably it is expanded perlite which has been quickly heated to above 871°C in order to allow for expansion and then subsequently cooled.

25 The perlite preferably has an abrasion value of 125 to 150 using RDA, (J Dent Res 37: 1060-1068, 1958 or J Dent Res 55:563 to 573, 1976.). Preferably the perlite is E 50 perlite available from Worldminerals Italia srl., Alzaia Trento 6, 20094 Corsico, Milano, Italy.



J7158 (V) FF

- 8 -

The perlite composition preferably contains  $\text{SiO}_2$  70-75% w/w,  $\text{Al}_2\text{O}_3$  10-15% w/w,  $\text{Fe}_2\text{O}_3$  0.5-1% w/w,  $\text{Na}_2\text{O}$  4-5% w/w,  $\text{K}_2\text{O}$  7-9 % w/w,  $\text{CaO}$  0.2-0.4% w/w,  $\text{MgO}$  0.05-1.5% w/w,  $\text{TiO}_2$  0.05-1.5% w/w.

- 5 The perlite is added to the elastomer during its processing, preferably the perlite is added to the resilient element while the elastomer is being readied in the masterbatch prior to injection moulding. Most preferably the perlite is added to the compounder at the same time as any colourants.

10

According to another embodiment of the present invention the perlite is present from 0.01% to 50% v/v of the elastomer.

Preferably the perlite is present from 10% to 30% v/v of the elastomer. Most preferably the perlite is present from 15%

15 to 25% v/v of the elastomer.

In its expanded form the perlite has a high porosity with a large available surface area thereby increasing the surface area to volume ratio. These properties mean that a

- 20 relatively small weight percent of perlite has such a large surface area that it gives effective whitening and other tooth polishing benefits at low weight levels.

According to another embodiment of the invention the perlite is present from 0.01% to 10% w/w of the elastomer.

25

Preferably the perlite is present from 1% to 8% w/w of the elastomer. Most preferably the perlite is present from 2% to 4% w/w of the elastomer.

- 30 The porosity of the perlite means that it is a relatively lightweight particle.



J7158 (V) FF

- 9 -

Therefore it is less likely to deform the resilient element during production or use of this element. As a result of this there is less chance of flex fatigue occurring in the resilient element because the stacks of perlite do not  
5 interfere with its resilient properties.

According to another preferred embodiment the weight median particle diameter of the perlite is from 10  $\mu\text{m}$  to 50  $\mu\text{m}$ . Preferably the weight median particle diameter is from 20  $\mu\text{m}$   
10 to 45  $\mu\text{m}$ . Most preferably the weight median particle diameter of the perlite is from 30  $\mu\text{m}$  to 40  $\mu\text{m}$ .

Preferably 90% by weight of the perlite has a particle diameter less than 70  $\mu\text{m}$  to 110  $\mu\text{m}$ . Preferably 10% by  
15 weight of the perlite has a particle diameter less than 7  $\mu\text{m}$  to 10  $\mu\text{m}$ . The particle size distribution of the perlite is determined using laser light scattering (Malvern 3600E, 300mm Lens).

20 According to another preferred embodiment the perlite has a bulk density of 100 to 180 g/l.

The bulk density of the perlite can be 50 to 350 g/l. Preferably the perlite has a bulk density of 70 to 200 g/l.  
25 Most preferably the bulk density of the perlite is 80 to 110 g/l. The bulk density of the perlite is measured by starting with homogeneous perlite particles, a set amount is then weighed and then it is shaken to pack it down. The volume that it occupies is measured and this is then divided  
30 by the weight.

J7158 (V) FF

- 10 -

The particles of perlite according to the present invention disperse effectively into the elastomer when the perlite is added to the elastomer. This dispersion of the perlite in the elastomer means that their cleaning benefit is

5 consistent on the teeth that they contact. This property of the perlite also means that the interference that the perlite has with the binding of the elastomer to the handle and or head of the polypropylene toothbrush skeleton is minimised as there will not be pockets of perlite that can

10 disadvantageously interfere with this interaction. The binding of the elastomer to the handle or head of the toothbrush is also aided by the alignment and shape of the perlite particles.

15 Preferred resilient element materials are thermoplastic elastomers for ease of injection moulding. The elastomer is made of a polymer material, such as a block co-polymer, preferred block co-polymers include polyolefins (for example polypropylene/ethylene propylene diamine modified systems

20 (i.e. synthetic rubber)), polyamides (for example polyamide (2 or polyamide 6), polyesters (for example polyester ester or polyether ester), polyurethanes (for example polyesterurethane, polyetherurethane or polyesteretherurethane). According to another preferred

25 embodiment the elastomer comprises a styrene block copolymer. Preferred styrene block copolymers include for example styrene ethylene butadiene styrene, or styrene butadiene styrene.

30 Elastomer materials can be two phase systems, which contain an internal phase material in a continuous phase of another

J7158 (V) FF

- 11 -

material. A particularly preferred example of this is the polypropylene/ethylene propylene diamine modified material described above, which is commercially available as Santoprene PPA (ex Advanced Elastomer Systems). Such two  
5 phase materials may conveniently have a continuous external thermoplastic phase, with the internal phase typically containing particles which may be in the order of 0.5µm to 5µm across.

10 To facilitate and simplify bonding of the resilient element to the head, the head may be made of materials which are of similar or even the same character, so that they for example have similar functional groups, similar levels of functionality, similar surface energies, and so on. Such  
15 similarity may facilitate adhesion of the respective components.

Alternatively, one or more components can be chemically modified by a chemical surface treatment to facilitate its  
20 adhesion to an adjacent component such as surface oxidation (e.g. by flaming, or by electrical discharge).

According to another preferred embodiment the elastomer has a Shore A hardness of 5 to 80. Preferably the elastomer has  
25 a Shore A hardness of 20 to 50. Most preferably the elastomer has a Shore A hardness of 25 to 35

The resilient material needs to be a material soft enough to provide whitening and polishing benefit to the teeth and to  
30 increase the efficacy of the toothbrush without having a negative impact on the gums and enamel.

J7158 (V) FF

- 12 -

According to another aspect of the present invention there is provided the use of a toothbrush according to any preceding claim for whitening teeth.

- 5 Embodiments of particular toothbrushes according to the invention will now be described in more detail with reference to the following figures.

Figures 1a and 1b show a single toothbrush in various views.

- 10 Figure 1a is an elevational view of the head and part of the handle of a toothbrush according to the invention. Figure 1b is a plan view of the toothbrush according to the invention as shown in figure 1a.

- 15 Figure 2, figure 3 and figure 4 are cross-sections along the line X to X' in figure 1b of the resilient member according to the invention.

- Figure 1a shows a toothbrush comprising a handle (1) and a  
20 head (2). The head has a bristle bearing surface (2a) from which extend bristles (3).

- Figure 1b shows a toothbrush according to figure 1a additionally showing an upstanding resilient element in the  
25 form of a wall-like structure (4). The wall-like structure (4) is shown in plan view but it clearly runs along a significant length of the head (2) and, in plan view, appears longer than the length of the head. The bristles (3) extend further from the head (2) than the wall-like  
30 structure (4).

J7158 (V) FF

- 13 -

Figure 2 shows a cross-sectional view of a wall-like structure (4) which tapers away from the bristle bearing surface (2a) of the brush head (2). By tapered away from the brush head is meant that the wall-like structure has a base (4a) and a tip (4b) and the distance across the base (B) is greater than the distance across the tip (T).

Figure 3 shows a wall-like structure (4) with a ridge (5) running along the tip. It may or may not be that the ridge runs along the entire length of the member.

Figure 4 shows a wall-like structure (4) which has a rounded surface (6). By rounded it is meant that there are no square edges on the structure.

15

J7158 (V) FF

- 14 -

## Claims:

1. A toothbrush comprising a resilient element, said resilient element comprising an elastomer into which is  
5 incorporated an abrasive, characterized in that the abrasive is perlite.
2. A toothbrush as claimed in claim 1, in which the perlite  
is present from 0.01% to 50% v/v of the elastomer.
- 10 3. A toothbrush as claimed in any of claims 1 and 2, in which the perlite is present from 0.01% to 10% w/w of the elastomer.
- 15 4. A toothbrush as claimed in any of claims 1 to 3, in which the median particle diameter of the perlite is from 10 to 50  $\mu\text{m}$ .
5. A toothbrush as claimed in any of claims 1 to 4, in which  
20 the resilient element is wall-like.
6. A toothbrush as claimed in any of claims 1 to 5, in which the elastomer comprises a styrene block copolymer.
- 25 7. A toothbrush as claimed in any of claims 1 to 6, in which the elastomer has a Shore A hardness from 5 to 80.

J7158 (V) FF

- 15 -

8. A toothbrush as claimed in any of claims 1 to 7 in which the perlite has a bulk density of 100 to 180 g/l.

9. The use of a toothbrush according to any preceding  
5 claim for whitening teeth.

J7158 (V) FF

- 16 -

Abstract

A toothbrush comprising a resilient element, said resilient  
element comprising an elastomer into which is incorporated  
5 an abrasive, characterized in that the abrasive is perlite.



Figure 1a.




Figure 1b




Figure 2




Figure 3




Figure 4

